

DK HDPE Smooth Geomembrane

HDPE is a smooth high density polyethylene (HDPE) geomembrane manufactured with the highest quality resin specifically formulated for flexible geomembranes. This product is used in applications that require excellent chemical resistance and endurance properties.

AT THE CORE:

HDPE geomembrane suitable for applications that require excellent chemical resistance and endurance properties.

Product Specifications

Tested Property	Test Method	Frequency	Minimum Average Value	
Product Code			HDPE	HDPE
Thickness, mm ⁽¹⁾	ASTM D 5199	every roll	0.3	0.5
Density, g/cm ³	ASTM D 1505 / D 792	every 5th roll	0.94	0.94
Tensile Properties (each direction) Strength at Break, N/mm-width Strength at Yield, N/mm-width Elongation at Break, % Elongation at Yield, %	ASTM D 6693, Type IV Dumbbell, 50 mm/min G.L. 51 mm G.L. 33 mm	every 5th roll	8 4 600 12	14 7 700 12
Tear Resistance, N	ASTM D 1004	every 5th roll	40	65
Puncture Resistance, N	ASTM D 4833	every 5th roll	105	176
Carbon Black Content, % (Range)	ASTM D 4218 / D 1603	every 5th roll	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D 5596	every 5th roll	Note ⁽²⁾	Note ⁽²⁾
Notched Constant Tensile Load, hours ⁽³⁾	ASTM D 5397, Appendix	90,000 kg	500	500
Oxidative Induction Time, minutes	ASTM D 3895, 200°C; O ₂ , 1 atm	90,000 kg	> 100	> 100

NOTES:

- ⁽¹⁾ Minimum Average Thickness and the lowest individual reading: Nominal -10%.
- ⁽²⁾ Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Categories 1 or 2. No more than 1 view from Category 3.
- ⁽³⁾ Stress crack resistance(NCTL) test is conducted on representative samples of the same resin formulation and in thicker gauge.
- ⁽⁴⁾ Roll lengths and widths have a tolerance of ±1%.

This Information is provided for reference purposes only and is not intended as a warranty or guarantee. assumes no liability in connection with the use of this Information. Specifications subject to change without notice.