

Property	M20-15	M30-20	M40-28	M50-35	M60-42	M80-56	M100-70
Breaking Strength in MD KN/m	20	30	40	50	60	80	100
Breaking Strength in MD KN/m	15	22	28	35	42	56	70
Elongation Rate	25%						
Trapezoidal Tearing Strength, KN >=	0.2	0.27	0.34	0.41	0.48	0.6	0.72
CBR Mullen Burst Strength KN	1.6	2.4	3.2	4	4.8	6	7.5
Vertical Permeability cm/s	$10^{-1} \sim 10^{-4}$						
Sieve Size O90 (O95) (mm)	0.07~0.50						
Unit Weight (g/m ²)	120	160	200	240	280	340	400
Variation	±10%						